



- **EPDM RETARDANTE DE LLAMA UL94 HBF**
EPDM FLAME RETARD UL 94 HBF
- **ALTAMENTE RESISTENTE A TEMPERATURAS, AGENTES ATMOSFÉRICOS CON PROPIEDADES RETARDANTES A LA LLAMA**
EXCELLENT RESISTANCE TO HIGH TEMPERATURES AND ATMOSPHERIC AGENTS, WITH FLAME-RETARDANT PROPERTIES



CAMPOS DE APLICACIÓN APPLICATIONS

- Automoción
- Calefacción y aire acondicionado
- Ferrocarril
- Construcción (carpintería de puertas y ventanas-aislamiento)
- Aeroespacial
- Naval
- Máquinas de movimiento de tierras
- Máquinas herramienta
- Eléctrico
- Fotovoltaica
- Energía eólica
- Electricidad
- Deportes
- Prevención de accidentes
- Automotive
- Heating-conditioning
- Railway
- Construction (fixtures-insulation)
- Aerospace
- Naval
- Constructions Equipment
- Machine tools
- Electric
- Photovoltaic
- Wind energy
- Electric energy
- Sporty
- Safety



FORMATOS DISPONIBLES AVAILABLE FORM



Rollos / Rolls



Placas / Sheets



Perfiles / Profiles



Barras / Bars



ESPECIFICACIONES TÉCNICAS TECHNICAL DATA SHEET

	NORMAS / STANDARD	VALORE / RESULTS
 Tipo de material Material Base		EPDM/CR
 Estructura celular Cells structure		Células Cerradas Closed Cells
 Color Color		Negro / Black
 Densidad Density	ISO 845	130 ± 25 kg/m ³
 Carga Deformación Compression Deflection	ASTM D-1056	25% 40 ± 15 kPa 50% 120 ± 40 kPa
 Compresión Compression Set	ASTM D-1056 23°C, 50% after 24h	≤ 25%
 Absorción de agua Water Absorption	ASTM D-1056	< 5%
 Dureza Hardness	ISO 868	35 ± 6 Sh 00
 Temperatura Temperature	Constante / Constant Intermitente / Intermittent	-40°C / +100°C +120°C
 Resistente a Resistance to	Ozono, abrasión e intemperie. Ozone, abrasion and weathering.	
 Certificaciones Certifications	UL94 HBF (5 mm) FVMUSS 302 Passed ≥ 3 mm	
 Normas medioambientales Environmental Protection	REACH RoHS CMRT	