



# L/CR NR/SBR (CONF. EN-1337-3 CE)

## PLACCHE APPOGGI

## PLATES



- **Caratteristiche corrispondenti al capitolato EN-1337-3CE.**

Characteristics pursuant to specification EN-1337-3 CE.



### IMPIEGO APPLICATIONS

Caratteristiche corrispondenti al capitolato EN-1337-3CE. Utilizzata comunemente come antivibrante e appoggio nelle strutture portanti. Particolarmente indicata per sopportare carichi molto elevati assorbendo contemporaneamente gli spostamenti orizzontali delle strutture edili. Discreta resistenza all'abrasione ed alla lacerazione, idonea a sopportare sollecitazioni ripetute (flessioni e vibrazioni), discrete caratteristiche fisico meccaniche. Buona resistenza agli agenti atmosferici ed all' ozono.

**Superficie:** Liscia/Liscia.

Characteristics pursuant to specification EN-1337-3 CE. They are commonly used for anti-vibration and to support load-bearing structures. In particular, they are indicated to support very heavy loads, simultaneously absorbing horizontal movements in buildings. They offer fair resistance against abrasion and laceration. They withstand repeated stress (flexion and vibrations) and have fair physical and mechanical characteristics. Good resistance against atmospheric agents and ozone.

**Surface:** Smooth/Smooth



mm  
5 ÷ 100

### STOCK

--



m  
≤ 1.20



m  
≤ 2.35



DUREZZA  
HARDNESS

Norme /  
Norms:  
ASTM  
D2240

60 Shore  
A ± 5



CARICO  
ROTTURA  
TENSILE  
STRENGTH

Norme /  
Norms:  
ASTM  
D412

160 kg/cm<sup>2</sup>



ALLUNGAMENTO  
ELONGATION

Norme /  
Norms:  
ASTM  
D412

425%



LACERAZIONE  
TEAR

Norme /  
Norms:  
ASTM  
D624

30 kg/cm



COMPRESSIONE  
COMPRESSION  
24 h - 70°C

Norme /  
Norms:  
ASTM  
D395-B

30%



PERDITA DI  
ABRASIONE  
ABRASION LOSS

Norme /  
Norms:  
ISO 4649

150 mm<sup>3</sup>



1,25 gr/cm<sup>3</sup>



-25°C / +85°C  
-13°F / +185°F