



L/NR 60 ABRATEX

CON SOTTOSTRATO

WITH BONDING LAYER



IMPIEGO APPLICATIONS

Utilizzata comunemente come rivestimento di tamburi metallici nel settore dei nastri trasportatori, o come protezione di superfici metalliche. Particolarmente indicata per offrire una discreta resistenza all'abrasione ed alla lacerazione, idonea a sopportare sollecitazioni ripetute (flessioni e vibrazioni), discrete caratteristiche fisico meccaniche. Viene fornita con un leggero spessore di gomma cruda da un lato che a contatto con una speciale soluzione (processo di vulcanizzazione a freddo) permette un eccezionale attacco gomma metallo.

Superficie: Liscia/Con sottostrato. A richiesta Liscia/Liscia o Liscia/I.T.

Commonly used as a coating on metal drums in the conveyor belt sector or to protect metal surfaces. In particular, it is indicated to offer fair resistance against abrasion and laceration. It withstands repeated stress (flexion and vibrations) and has fair physical and mechanical characteristics. It is supplied with a thin layer of raw rubber on one side which, in contact with a special solution (cold vulcanization process) gives exceptional rubber-metal attachment.

Surface: Smooth/With bonding layer. On request, Smooth/Smooth or Smooth/I.T.

 mm	STOCK	 m	 m
5	✓	1,4	20
6	✓	1,4	20
8	✓	1,4	20
10	✓	1,4	20
12	--	1,4	10
15	✓	1,4	10
20	✓	1,4	10



DUREZZA
HARDNESS



CARICO ROTTURA
TENSILE
STRENGTH



ALLUNGAMENTO
ELONGATION



LACERAZIONE
TEAR



COMPRESSION
24 h - 70°C



PERDITA DI ABRASIONE
ABRASION LOSS

Norme / Norms: ASTM D2240 Norme / Norms: ASTM D412 Norme / Norms: ASTM D412 Norme / Norms: ASTM D624 Norme / Norms: ASTM D395-B Norme / Norms: ISO 4649

60 Shore A ± 5 150 kg/cm² 350% 25 n/mm 50% <130 mm³



1,2 gr/cm³



-25°C / +80°C
-13°F / +176°F