



IMPIEGO APPLICATIONS

Utilizzata comunemente per rivestimento di cicloni tramogge. Viene fornita con due lati molati o con un lato in gomma cruda per la vulcanizzazione a freddo tramite soluzione specifica la quale conferisce un'eccezionale attacco gomma-metallo. Eccellente resistenza all'usura, l'incredibile elasticità e alto carico di rottura della gomma le permette di sopportare le forti sollecitazioni che subisce durante il lavoro.
Superficie: Molata/Molata a richiesta: Liscia/molata, Liscia/Liscia, Liscia/con sottostrato crudo, liscia/impressione tela.

Its particular and unique compound gives at this sheet, superior performance in abrasion condition. The super clicloni red is extremely versatile and suitable as protective lining for a variety of surfaces to minimise wear and corrosion of the base structure. Typical lining applications include: chute lining, pipe lining, vessel lining, hose construction, hydrocyclones, conveyor systems, material handling systems and grinding mills.




Surface: grinded/grinded on request: smooth/grinded, smooth/smooth, smooth/with raw underlayer, smooth/I.T.

L/NX SUPER CICLONI RED



 mm	STOCK	 m	 m
3	--	1,4	10
5	✓	1,4	10
6	✓	1,4	10
8	✓	1,4	10
10	✓	1,4	10
12	--	1,4	10
15	--	1,4	10
20 / 25	--	1,4	10

 DUREZZA HARDNESS	 CARICO ROTTURA TENSILE STRENGTH	 ALLUNGAMENTO ELONGATION	 LACERAZIONE TEAR	 COMPRESSION 24 h - 70°C	 PERDITA DI ABRASIONE ABRASION LOSS
Norme / Norms: ASTM D2240	Norme / Norms: ASTM D412	Norme / Norms: ASTM D412	Norme / Norms: ASTM D624	Norme / Norms: ASTM D395 B	Norme / Norms: ISO 4649
35 Shore A ± 5	200 kg/cm ²	800%	140 kg/cm	30%	60 mm ³



0,95 gr/cm³

-25°C / +80°C
-13°F / +176°F